



TEXTILE PRINTING

TEXIPLAST 7000 MS

Código N° 165800

INFORMACIONES TÉCNICAS

Tintas plastisol para la impresión textil.

- Exento de ftalatos, nonilfenoles y metales pesados.
- Disponibilidad de sistema de mezcla con CD y báscula.
- Opacos, brillantes y suaves para la impresión directa.
- Elevada estampabilidad mojado sobre mojado.
- Rápido secado intermedio (flash-cure)

PREPARACION : las tintas están listas para el uso.
La viscosidad se puede reducir, sin comprometer la opacidad, con máx. 2% de TEXIPLAST ADITIVO 554.

COLORES : 13 colores de la carta de colores más Blanco Flash Cure.
Los colores se pueden mezclar entre si en cualquier proporción.
Recomendamos no mezclar la serie 7000 MS con otros aditivos o productos de otras series de plastisol para tener la garantía de la ausencia de ftalatos.
En la realización de colores pálidos, se recomienda verificar la constancia en el tiempo.

IMPRESION : Pantallas serigráficas máx. 90 hilos/cm.

LIMPIEZA : Pantallas y utillajes se limpian con white spirit o con SCREENCLEAN ST.

POLIMERIZACIÓN : Para todos los colores, temperatura 140-150°C, tiempo 2-4 minutos.

LAVADO : operando en las condiciones de polimerización mínimas, se alcanza una resistencia al lavado domestico a 60°C.

CONFECCIONES : 1, 5 Kg

NOTA IMPORTANTE: **TEXIPLAST 7000 MS** ES UNA SERIE QUE SE PUEDE CONTAMINAR FÁCILMENTE; ANTES DE LA IMPRESIÓN CONVIENE ASEGURARSE QUE RASCLES, ESPÁTULAS, PANTALLAS Y ENVASES ESTEN LIMPIOS DE RESIDUOS DE OTRAS SERIES DE PLASTISOL.

Las anteriores informaciones son el resultado de pruebas escrupulosamente controladas y expresan nuestros mejores y más actualizados conocimientos. En cualquier caso, estas noticias se dan a conocer únicamente como información sin que ello suponga compromiso alguno por parte de nuestra Empresa ni dar lugar a reclamaciones de cualquier tipo que puedan derivarse del empleo de los productos descritos. Teniendo en cuenta asimismo que las condiciones de uso se escapan de nuestro control.



Textile Printing



TEXIPLAST 7000 MS

Code N° 1658--

PRODUCT DESCRIPTION

Series of plastisol semi-opaque inks for textile printing with glossy finishing. With dedicated formulae for the realization of colour references

APPLICATION FIELDS

Direct and transfer textile printing. For ready-to-wear or pre-cut articles.

APPLICATION PROCESS

Substrates	<ul style="list-style-type: none"> • Cotton 100% • Cotton mixed with synthetic fibers <p>The substrates may be white or coloured</p>
Th/cm	Max: 90 Th/cm (230 Th/inch)
Emulsion	<ul style="list-style-type: none"> • ZERO - IN ASTRA • ZERO - IN UNIVERSAL PLUS
Squeegee	Square edge. Squeegee hardness, according to the desired final effect
Curing	150°C – 160°C for 3 minutes
Thinner	<ul style="list-style-type: none"> • Max 5% TEXIPLAST ADD.554 (VISCOREDUCER)
Thickening agent	In case, max 0,5% TEXIPLAST ADDENSANTE
Cleaning	SCREENCLEAN ST
Storage	<ul style="list-style-type: none"> • Away from direct sunlight • At a temperature between 15-35°C
Package	5 Kg
Safety Data Sheet	Available upon request



GENERAL FEATURES

- Mixing System with CD and Balance
- Excellent wet on wet printability
- Bright chromatic range
- Good elasticity
- Soft touch
- Phthalate-free

PREPARATION:

Ready-to-use ink.
Homogenize well, before using it. The colours may be all mixed among them with each ratio. It is however recommended not to mix more than 4 bases together at a time. When realizing soft colours, it is recommended to check their steadiness during time. The possible addition of **TEXIPLAST ADDITIVO 554** allows to reduce ink viscosity. The possible addition of **TEXIPLAST EXTENDER BASE PF (Max 60%)** allows to obtain matter effects with a soft touch, without compromising the opacity and the general fastness.

APPLICATION:

For the best colour opacity and brightness, during printing, it is recommended to adjust the out of contact and the pressure of the squeegee at their best, in order to obtain an ink film that can remain onto the surface of the substrate. The opacity is influenced by the kind of drawing, the th/cm screen number, the squeegee, the pressure and the printing speed.
The inks of the series **TEXIPLAST 7000 MS** are semi-opaque, the performances and the shades of the colours might be different, if they are printed onto coloured fabrics. In case of dark substrates, it is recommended to overprint the inks of the series **TEXIPLAST 7000 MS** onto a white background. For such application, the use **TEXIPLAST 7000 WHITE FLASH CURE** or **TEXIPLAST 7000 WHITE FLASH LT** (see the related technical data sheet) is recommended.

CURING:

Curing must take place at 150°C – 160°C for 3 minutes.

TEXIPLAST are thermoplastic inks: only an appropriate curing is able to allow the complete ink fusion, therefore the achievement of the required final characteristics.



Textile Printing



SPECIAL INSTRUCTIONS

- Always test the print characteristics, before starting production.
- Always check curing conditions. The addition of additives could require higher temperature or longer time.
- Plastisol inks do not resist dry cleaning, bleaching and ironing.
- The inks of the series **TEXIPLAST 7000** are PHTHALATE-free. Before using them, make sure that squeegees, countersqueegees, screens and cases have been cleaned well from possible rests of other plastisol series. In that way, possible "pollution", deriving from other ink series, can be avoided.

IMPORTANT NOTE

The information given in this technical sheet is not intended to be exhaustive and any person, using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us to the suitability of the product for the intended purpose, does so at his own risk. While we endeavour to ensure that all advice we give about the product is correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage arising out of the use of the product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

PRODUCT RANGE

CODE	TEXIPLAST 7000 MS	PACKAGE
165886	LIGHT BLUE	5 Kg
165887	NAVY BLUE	5 Kg
165889	BLACK	5 Kg
165891	LIGHT YELLOW	5 Kg
165892	YELLOW	5 Kg
165893	ORANGE	5 Kg
165894	SCARLET	5 Kg
165895	RED	5 Kg
165896	FUXIA	5 Kg
165897	VIOLET	5 Kg
165898	BLUE	5 Kg
165899	GREEN	5 Kg
165888	WHITE	5 Kg
CODE	TEXIPLAST 7000	PACKAGE
165882	WHITE FLASH CURE	5 and 25 Kg
165881	WHITE FLASH LT	5 and 30 Kg
165884	WHITE SUPER BRIGHT	5 and 30 Kg
165885	WHITE LF	5 and 30 Kg
167873	LYTHO TRANSF. BIANCO	1 and 5 Kg
CODE	TEXIPLAST 7000	PACKAGE
1658--	OP	5 and 30 Kg
16586-	PROCESS	1 and 5 Kg

FRICION FASTNESS

TEXIPLAST 7000 MS		LENGTH		WIDTH	
		DRY	WET	DRY	WET
165886	LIGHT BLUE	4	4	4	4
165887	NAVY BLUE	4	4-5	4	4
165889	BLACK	4-5	4-5	4-5	4-5
165891	LIGHT YELLOW	4	3-4	4	3-4
165892	YELLOW	4	4-5	4	4-5
165893	ORANGE	3-4	4	3-4	4
165894	SCARLET	3	2-3	4	3
165895	RED	3-4	3-4	3-4	3
165896	FUXIA	4	4	4	4
165897	VIOLET	4	4-5	4	4
165898	BLUE	4-5	3-4	4-5	3
165899	GREEN	4	4	4	4

UNI EN ISO 105 X12:2003

Some red and blue pigments, depending on the tone intensity, might show low washing or friction fastness, even in optimal curing conditions. Always check these characteristics, before starting production.

EQUIPMENT

Indicated for using onto automatic, semi-automatic and manual machines.

WARNING

This technical data sheet does not replace either the Safety Data Sheet or the specific Conformity Declaration. These documents may be required to our SHEQ (Product safety office), at the following e-mail address: safety@eptainks.com

The technical data sheet does not relieve the printer, who remains the only responsible of the respect of the regulations, the specifications and the related required certifications of the finished items.